



TECHNICAL DATA SHEET

[EVAGLOSS]

Modified Alkyd Gloss Enamel

PRODUCT DESCRIPTION

A professional exterior and interior range of modified alkyd solvent based enamel as decorative and protective coating for metal and wood surfaces suitable for new and repainting projects.

- ▶ Easy application.
- ▶ High gloss finishing.
- ▶ Superior algae and fungus resistance.
- ▶ Good durability.

DESIGN USE

☉ As a top coat for substrates such as metal and wood surfaces.

PHYSICAL DATA

VOLUME SOLIDS	35 ± 2%
DRY FILM THICKNESS (DFT)	30 µm / Coat
WET FILM THICKNESS (WFT)	85.71 µm / Coat
NUMBER OF COATS	2
THEORATICAL COVERAGE	11.67 m ² /L/coat
FINISH	High Gloss
COLOUR RANGE	Wide colour range (Please consult KCC Technical Department)
NO. OF COMPONENTS	1
STANDARD PACKING SIZE	1L, 5L, 15L

RECOMMENDED PAINTING SYSTEM

Substrate: Wood		
System	Product	No. of Coats
Undercoat	Alkyd 131UC / Eva Undercoat	1
Finish	Evagloss	2
Substrate: Metal		
System	Product	No. of Coats
Primer	Metal-Prime 212ROX / Metal-Prime 213ZP	1
Finish	Evagloss	2
Substrate: Previously Painted Wood, Metal		
System	Product	No. of Coats
Primer	Not Necessary	-
Undercoat	Not Necessary	-
Finish	Evagloss	2

APPLICATION METHOD

Brush, Roller or Spray application
* Stir the contents thoroughly before use. Thinning is normally not necessary. However, if required for better workability, do not exceed 5% dilution ratio. Clean up equipment with **Thinner 51** immediately after use.

DRYING TIME

Substrate Temperature	Touch Dry	Hard Dry	Overcoating Interval	
			Minimum	Maximum
15°C	6hr	12hr	8hr	-
25°C	4hr	9hr	6hr	-
35°C	2.5hr	6hr	4hr	-

ADDITIONAL INFORMATION

Thinner	Thinner 51
Thinning Ratio	Do not exceed 5% dilution ratio.
Cleaning Solvent	Thinner 51
Flash Point	35°C
Storage Requirements	Cool, dry and well ventilated area away from heat and direct sunlight(5~35°C). Lid must be kept tightly closed.



TECHNICAL DATA SHEET

[EVAGLOSS]

Modified Alkyd Gloss Enamel

SURFACE PREPARATION

Metal

- ◆ The substrate must be sound and free from dirt, grease, oil, dust, and any contaminations.
- ◆ All traces of form release agent/ curing agent must be removed.
- ◆ A light sanding with suitable abrasive material is recommended before application.
- ◆ Any resulting dust / loose particles must be removed.
- ◆ The scraped areas should be spot-primed with a metal primer.

Wood

- ◆ Wood substrate must be sound and free from dirt, grease and any contaminations.
- ◆ Scrape off all loose woodwork and all protrusions must be rounded-off.
- ◆ Fill nail-holes and minor imperfections with an appropriate wood putty.
- ◆ Sand smooth with #320 sandpaper.
- ◆ The scraped areas should be spot-primed with a wood surface undercoat.

Previously Painted Surfaces

- ◆ All loose or defective paintwork or powdery residues shall be thoroughly removed by suitable abrasive material, make good defective areas.
- ◆ A light sanding with suitable abrasive material is recommended before application.
- ◆ Any resulting dust / loose particles must be removed.

Application conditions

- ◆ Ensure the surface is completely clean and dry.
- ◆ Ensure the relative humidity below 90% before painting.
- ◆ Ensure the surface temperature at least 3°C above dew point temperature.

Remark

- ☞ Always conduct an application point test on small area. Check for any abnormalities and paint defects prior to painting.
 - ☞ This product should only be applied over concrete, plaster and masonry substrate that have been suitably sealed and primed.
 - ☞ Avoid excessive thinning as it will result in colour difference, poor hiding power, poor finishing, and overall paint performance compromised.
 - ☞ Always follow TDS recommended coating thickness and ensure uniform application thickness. Inconsistent film thickness will result in difference sheen level and unpleasant finishing.
 - ☞ It is recommended to paint the same colour with same batch number, using same painting equipment and method and also follow instructed thinning ratio to ensure consistent painted finishing.
 - ☞ Recommended to paint according to TDS and Application guide.
- (Please consult with KCC customer service for any inquiries or browse to our website www.kccpaint.com.my)*

SAFETY PRECAUTIONS

- ◆ This product is flammable.
- ◆ Ensure adequate ventilation during application and drying.
- ◆ Avoid contact with eyes and skin.
- ◆ In case of contact with skin, wash immediately with plenty of soap and water.
- ◆ During spray application, do not breathe in mist and wear suitable respiratory protective equipment.
- ◆ Keep out of reach of children.

FIRST AID

- | | |
|-------------------|---|
| Eyes | Rinse immediately with plenty of water and seek medical advice. |
| Skin | Wash immediately with plenty of soap and water. |
| Inhalation | Remove to fresh air, loosen collar and keep patient rested. |
| Ingestion | DO NOT INDUCE VOMITING. Obtain medical attention. |

DISCLAIMER

The above information is given to the best of our knowledge based on laboratory testing and practical experiences. The information in this data sheet may be subject to changes from time to time and without notice due to production refinements arising from continuing research and evaluation programmes, which may occasionally result in marginal changes in the coating properties.